

Bitumen Viscosity VG-30

Bitumen Viscosity VG-30			
BINDER PROPERTIES	REQUIREMENTS		TEST METHOD
	MIN	MAX	
Absolute viscosity @ 60 °C, Pa.s	240	-	ASTM D-2171
Kinematic viscosity@135°C, mm ² /s	350	-	ASTM D-2171
Flash point, °C	230	-	ASTM D-92
penetration @25°C	50	70	ASTM D-5
Softening point °C	47	-	ASTM D-36
Solubility in trichloroethylene, %	99.0	-	ASTM D-2042
Test on Residue from thin film oven tests			
Ductility @ 25°C cm	40	-	ASTM D-113
viscosity Ratio @ 60 °C Pa.s	-	1500	ASTM D-2171

Packing:

- 180(Kg) new steel drum.
- 220(Liter) new steel drum.
- Jumbo Bag 1000(kg), 300(kg) and 250(kg).