

## Bitumen Viscosity VG-40

<b>Bitumen Viscosity VG-40</b>			
<b>BINDER PROPERTIES</b>	<b>REQUIREMENTS</b>		<b>TEST METHOD</b>
	<b>MIN</b>	<b>MAX</b>	
Absolute viscosity @ 60 °C, Pa.s	320	480	ASTM D-2171
Kinematic viscosity@135°C, mm <sup>2</sup> /s	400	-	ASTM D-2171
Flash point, °C	230	-	ASTM D-92
penetration @25°C	40	60	ASTM D-5
Softening point °C	50	-	ASTM D-36
Solubility in trichloroethylene, %	99.0	-	ASTM D-2042
Test on Residue from thin film oven tests			
Ductility @ 25°C,cm	25	-	ASTM D-113
viscosity Ratio @ 60 °C, Pa.s	-	2000	ASTM D-2171

### Packing:

- 180(Kg) new steel drum.
- 220(Liter) new steel drum.
- Jumbo Bag 1000(kg), 300(kg) and 250(kg).