



بيتولاين تریدینگ ال ال سی

## Slow curing cutback bitumen SC-70

### Slow curing cutback bitumen SC-70

property	Min	Max	Test Method
kinematic viscosity at 60°C mm <sup>2</sup> /s	70	140	ASTM D2170
Flash point (tag open-cup), °C	66	-	ASTM D3143
distillate test: distillate, volume percent of total distillate at 360°C:			
Total distillation up to 360 ° C, volume%	10	30	ASTM D402
test on residue from distillation:			
viscosity at 60°C	400	7000	
penetration at 25°C	50	-	ASTM D5
ductility at 25°C	100	-	ASTM D113
solubility in trichloroethylene, %	99.0	-	ASTM D2042
Water,%	-	0.5	ASTM D95